

NOVA BAG

PROPERTY	UNIT	STANDARD	TOLERANCE	VALUES
GRAMMAGE	g/m ²	ISO 536	±3%	190
CALIPER	pt	ISO 534	±0.4	9.6
THICKNESS	μm	ISO 534	±10	245
STIFFNESS CD	mNm	ISO 2493	≥	1.60
STIFFNESS MD	mNm	ISO 2493	≥	3.50
MOISTURE	%	ISO 287	±1.0	6.0
PPS TOP	μm	ISO 8791-4	≤	1.40
BRIGHTNESS TOP	%	ISO 2470-2	±2.0	90.0
BRIGHTNESS BACK	%	ISO 2470-2	±2.0	85.0
GLOSS 75° TOP	%	ISO 8254-1	≥	45
IGT BLISTER TOP	m/s	ISO 3783	≥	1.50
COBB 60s Top	g/m ²	ISO 535	±15.0	40.0
COBB 60s Back	g/m ²	ISO 535	±15.0	40.0
PLY Bonding	J/m ²	TAPPI 569	≥	130
Squareness	mm	GB/T 451.1		0-0.2
Size Deviation	mm	GB/T 451.1		0-0.2