

MARKS &
SPENCER

Organic penne

from the grocery...

There's a century of passion and experience behind this special pasta, made for us by a family-run firm in northern Italy. The purest Sicilian durum wheat is mixed with spring water from 2000m up Mount Latemar in Val di Fiemme. The pasta is shaped using a bronze die, giving it a rough texture that's perfect for soaking up sauces, then slowly dried in the pure, clean air of the Dolomites.



KA ALIMENTARE

NOVA AVANA


STAMPATO su cartoncino KA ALIMENTARE- 250 gr.

KA ALIMENTARE

- ECCELLENTI RIGIDITÀ E SPESSORE
- ELEVATO PUNTO DI BIANCO ANCHE SUL RETRO
- OTTIME PERFORMANCE NEL CONFEZIONAMENTO AUTOMATICO
- CERTIFICATO PER PACKAGING ALIMENTARE

KA ALIMENTARE

NOVA AVANA

KA	CARTONCINO TRIPLEX PATINATO, RETRO KRAFT ALIMENTARE / GT4 FULLY COATED WHITE LINED CHIPBOARD, KRAFT BACK FOR DRY FOOD CONTACT / GT4
	<p>Doppia Patinatura – Pigmenti Naturali <i>Double Coating – Natural Pigments</i> 100% Macero Selezionato Bianco <i>100% Selected White Waste Paper</i></p> <p>100% Macero Selezionato <i>100% Selected Waste Paper</i></p> <p>100% Macero Selezionato Kraft <i>100% Selected Waste Paper</i></p> 

GRAMMATURA SUBSTANCE	SPESSORE CALIPER	VOLUMINOSITA' BULK	RIGIDITA' TABER STIFFNESS TABER		RIGIDITA' TABER STIFFNESS TABER		RIGIDITA' DIN (*) STIFFNESS DIN	
			g/m ²	microns	cm ³ /g	g.cm		mN.m
			LONG-MD	TRASV-CD	LONG-MD-SM	TRASV-CD	LONG-MD	TRASV-CD
290	380	1,31	120.0	46.0	11.8	4.5	22.7	8.3
320	425	1,33	165.0	59.0	16.2	5.8	31.4	10.8
350	460	1,31	205.0	78.0	20.1	7.7	39.2	14.5
385	510	1,32	255.0	100.0	25.0	9.8	48.9	18.8
400	530	1,33	276.0	110.0	27.1	10.8	53.0	20.7
435	575	1,32	330.0	140.0	32.4	13.7	63.5	26.6
450	600	1,33	370.0	150.0	36.3	14.7	71.2	28.5
500	670	1,34	470.0	190.0	46.1	18.6	90.7	36.3
550	730	1,33	585.0	260.0	57.4	25.5	113.0	49.9

CONDIZIONI DI FORNITURA: QUANTITÀ MINIMA PER ORDINE TON.10 + FORMATI AUTOABBINABILI O LUCE MACCHINA
 SUPPLY CONDITIONS: ORDER MINIMUM QUANTITY TON 10 + SELF COMBINED OR WIDTH MACHINE SIZES

CONDIZIONI AMBIENTALI – TESTING CLIMATE CONDITIONS (UNI EN 20187:1994): T 23°C - RH 50%

CAMPIONAMENTO – SAMPLING	UNI EN ISO 186:2003	TOLLERANZE - TOLERANCES 95% DEI VALORI – 95% OF VALUES	
GRAMMATURA - SUBSTANCE	UNI EN ISO 536:2012	- 3%	+ 3%
SPESSORE – CALIPER	UNI EN ISO 534:2012	- 5%	+ 5%
VOLUMINOSITA' – BULK	UNI EN ISO 534:2012	- 5%	+ 5%
RIGIDITA' - STIFFNESS (*) I valori Taber sono misurati; i valori DIN sono calcolati. Taber figures are measured; DIN figures are calculated	ISO 2493-1:2010 ISO 2493-2:2011 DIN 53121:2014-08	- 15%	

		VALORI – VALUES	
		MIN	MAX
BIANCO COPERTINA - TOP BRIGHTNESS	UNI ISO 2470-1:2016 UNI ISO 2470-2:2010	80%	84%
STRAPPO IGT - DRY PICK IGT (M.V. OIL)	UNI ISO 3783:2008	50 cm/sec	
CLASSIFICAZIONE CARTONE - BOARD CLASSIFICATION	DIN 19303: 2011-03		



NOVA POPYRA

Paper Solutions & Services

NOVA POPYRA SRL

VIA 1° MAGGIO, 3 37069 VILLAFRANCA DI VERONA

TEL: 045/6304992 FAX: 045/6309254

info@novapopyra.it www.novapopyra.it



FSC® C110470



www.pefc.it

