

NOVABOX FSC

GC2

Grammatura Grammage Grammage	Calibro Caliper Épaisseur	Volume Bulk Main	Rigidità / Stiffness / Rigidity				Umidità moisture humidité
			DIN (L&W 5°)		Taber 15°		
			längs / md / sm	quer / cd / st	längs / md / sm	quer / cd / st	
[g/m ²]	[µm]	[cm ³ /g]	[mNm]	[mNm]	[mNm]	[mNm]	[%]
230	400	1,74	22,6	8,7	12,0	4,6	8,5
250	440	1,76	28,6	11,2	15,2	6,0	8,5
265	460	1,74	33,5	13,2	17,8	7,0	8,5
280	495	1,77	38,7	15,4	20,5	8,2	8,5
300	525	1,75	46,3	18,6	24,5	9,9	8,5
325	570	1,75	56,6	23	29,7	12,3	8,5
350	615	1,76	68	27,7	35,4	14,7	8,5
370	645	1,74	77,8	31,9	40,2	16,9	8,5
400	700	1,75	93,7	38,6	47,8	20,5	8,5



NOVA POPYRA

Paper Solutions & Services

NOVA POPYRA SRL

VIA 1° MAGGIO, 3 37069 VILLAFRANCA DI VERONA

TEL: 045/6304992 FAX: 045/6309254

info@novapopyra.it www.novapopyra.it



Il marchio della
gestione forestale
responsabile



Promuoviamo la
Gestione Sostenibile
delle Foreste
www.pefc.it

