

NOVATREND

SILK

Proprietà	ISO						
Grammatura	(ISO 536)	(g/m ²)	65	70	75*	80	90
Spessore	(ISO 534)	(µm)	62	67	71	75	83
Mano	(ISO 534)	(cm ³ /g)	0.95	0.96	0.95	0.94	0.92
Grado di Bianco D 65	(ISO 2470)	(%)	92	93	94	94	95
Bianchezza CIE	(ISO 11475)	(%)	120	120	120	120	120
Tonalità L D 65	(ISO 5631-2)	(D65/10°)	93	93	94	94	94
Tonalità A D 65	(ISO 5631-2)	(D65/10°)	1.2	1.2	1.2	1.2	1.2
Tonalità B D 65	(ISO 5631-2)	(D65/10°)	-7.4	-7.5	-7.5	-7.5	-7.5
Opacità	(ISO 2471)	(%)	94	95	95	95	96
Lucido (Lehman)	(ISO 8254-1) (Tappi T480)	(%)	32	32	35	36	37
Liscio PPS 10	(ISO 8791-4)	(µm)	2.5	2.5	2.5	2.5	2.5

GLOSS

Proprietà	ISO						
Grammatura	(ISO 536)	(g/m ²)	65	70	75*	80	90
Spessore	(ISO 534)	(µm)	56	59	63	68	75
Mano	(ISO 534)	(cm ³ /g)	0.86	0.84	0.84	0.85	0.83
Grado di Bianco D 65	(ISO 2470)	(%)	92	92	92	93	93
Bianchezza CIE	(ISO 11475)	(%)	118	118	118	118	118
Tonalità L D 65	(ISO 5631-2)	(D65/10°)	92	93	93	93	93
Tonalità A D 65	(ISO 5631-2)	(D65/10°)	0.8	0.8	1.0	1.0	1.0
Tonalità B D 65	(ISO 5631-2)	(D65/10°)	-7.2	-7.2	-7.2	-7.8	-7.8
Opacità	(ISO 2471)	(%)	92	93	94	95	96
Lucido (Lehman)	(ISO 8254-1) (Tappi T480)	(%)	56	58	59	60	60
Liscio PPS 10	(ISO 8791-4)	(µm)	1.2	1.2	1.2	1.2	1.2



NOVA PAPYRA

Paper Solutions & Services

NOVA PAPYRA SRL

VIA 1° MAGGIO, 3 37069 VILLAFRANCA DI VERONA

TEL: 045/6304992 FAX: 045/6309254

info@novapapypira.it www.novapapypira.it



Promuoviamo la
Gestione Sostenibile
delle Foreste
www.pefc.it

