

PATINATA VILLA

Patinata Opaca VillaSilk			Specs							
			60	65	70	75	80	90	100	110
Brightness	D65/10* ISO 2770-2	%	92	93	94	95	96	97	98	99
Whiteness	CIE, ISO 11476 C2°	%	97	98	99	100	102	103	104	104
Opacity	D65/10° ISO 5471	%	91.5	92	93	94	95	96	97	97.5
Thickness	ISO 534	µm	61	64	67	72	75	85	94	104
Bulk	ISO 534	cm3/g	1	0.98	0.96	0.96	0.94	0.94	0.94	0.94

Patinata Lucida Villagoss			65	70	75	80	90	100	110
Brightness	D65/10* ISO 2770-2	%	91	92	93	94	95	96	97
Whiteness	CIE, ISO 11476 C2°	%	96	97	98	100	101	102	102
Opacity	D65/10° ISO 5471	%	91.5	92.5	93.5	94.5	96	97	97.5
Thickness	ISO 534	µm	55	58	61	65	73	81	86
Bulk	ISO 534	cm3/g	0.85	0.83	0.81	0.81	0.81	0.81	0.79

Patinata Bulk Villamatt Vol 1.1			65	70	75	80	85
Brightness	D65/10* ISO 2770-2	%	93	94	94	95	95
Whiteness	CIE, ISO 11476 C2°	%	98	99	100	100	101
Opacity	D65/10° ISO 5471	%	92	92.5	94	94.5	96
Thickness	ISO 534	µm	73	77	83	87	91
Bulk	ISO 534	cm3/g	> 1.05	> 1.05	> 1.05	> 1.05	> 1.05

NOTE:

- DISPONIBILI A STOCCARE A CENTRO TAGLIO BOBINE PER PROGETTI DEDICATI
- CERTIFICABILI FSC E PEFC



NOVA PAPYRA
Paper Solutions & Services

NOVA PAPYRA SRL
VIA 1° MAGGIO, 3 37069 VILAFRANCA DI VERONA
TEL: 045/6304992 FAX: 045/6309254
info@novapapya.it www.novapapya.it

